

规格承认书

Specification For Approval

客户名称:

(Customer Name)

产品名称:

(Product Name)

客户料号:

(Customer part number)

科尼盛料号:

(KNSCHA number)

型号规格:

(Specifications)

日期:

DATE

高分子固态电解电容器

Conductive Polymer Aluminum Electrolytic Capacitors

118EC225

PV 220 μ F/35V 6.3*12mm 3000H

2025.7.24

制 造 Manufacture	
核 准 APPROVAL	制 作 PREPARED
王帅	陈美秀

客户承认栏 CUSTOMER APPROVED		
核 准 APPROVED	确 认 CHECKED	经 办 DESIGNED

广东科尼盛电子科技有限公司

KNSCHA ELECTRONICS CO.,LIMITED.

No. 8th floor, A3 building, R&D center (Phase I),

Songshan Lake Intelligent Valley, Liaobu Town, Dongguan City.




TEL:0769-83698067 81035570 FAX: 0769-83861559

Email: sales@knscha.com Website: <http://www.knscha.com>




规格表Table


[illegible]

9	温度特性 Temperature Characteristics	  
---	-------------------------------------	---

四、测试方法及要求 Tests

1	浪涌测试 Surge testing	在标准温度条件下存放使其稳定，然后再测试。 he capacitor shall be subjected to 1000 cycles at a temperature specified below, each consisting of a charge period of 30±5sec, followed by a discharge period of approx. 5min30sec. And the capacitor shall be stored under standard conditions thermal to obtain stability,after which measurements shall be made. measurement circuit(测试电路图)				
				VZ: 浪涌电压 Surge voltage		
		R1: 保护电阻 (1KΩ) Protective resistor		V1: 直流电压 DC voltage		
		CX:测试电容 Test capacitor		R2: 放电电阻 Discharge resistor		
		S:开关 Switch				
		SPEC:		1) 电容量变化Change in capacitance: ±10%初时值以内Within±10% of the initial value		
				2) 损耗正切值tangent of the loss angle: 小于等于初时值≤The initial specified value		
				3) ESR (equivalent series resistance) : 小于等于初时值≤The initial specified value or less		
				4) 漏电流leakage current: 小于等于初时值≤The initial specified value or less		
		电压设定:		RATED VOLTAGE (V_{DC})		35
		SURGE VOLTAGE (V_{DC})		40.25		
2	端子强度	1) 拉力(tensile)		d(mm)	[N]	Duration time
				0.6	10	10±2sec(秒)
		2)抗弯强度 (Bending)				
		端子应该在每一个方向上折弯一次，总共两次				
		The terminal shall be subjected to 1 bend in each direction with a total 2 bends only.				
		d(mm)		[N]		
		0.6		5.0 (0.51KG)		
端子没有破损或松动 SPEC: No breaking and loosening of terminal						

3	可焊性 solderability	焊料(Solder) : H60A. H60S or(或)H63A
		焊接温度(Solder temperature) : 245±2℃
		浸入时间(Immersion time) : 3±0.5sec(秒)
		浸入深度(Immersion depth) : 离本体 1.5~2mm
		熔化: 松香在酒精的浓度是25% Flux: 25% by in densitg of rosin in ethanol
		从含浸处到顶部, 至少有3/4部分覆盖有新焊料
		SPEC:1)3/4 of the circumference of the surface up to the immersed shall be covered with
		new solder.
4	耐焊接热 Resistance to soldering hea	焊料: (Solder) : H60A.H60S or (或) H63A
		焊接温度(Solder temperature) : 350±10℃ (or 350±10℃)
		浸入时间(Immersion time) : 10±1sec(秒) (or 或 3.5±0.5sec)
		绝热遮罩板的厚度 (Thickness of heat shunt:1.6mm) : 1.6mm
		SPEC: 1)电容量变化Change in capacitance: ±10%初时值以内Within±10%of the initial
		value
		2)损耗正切角tangent of the loss angle:小于等于初始规定值≤The initial specified
		value
5	表示耐溶剂 性	标示应清晰可见
		试剂: 乙丙醇, 浸入时间30±0.5sec
6	高温高湿 Dampheat, steady state	电容器在温度60±2℃, 相对湿度90%到95%条件下存放240±8个小时, 然后在标准条件下放1
		到2小时后进行测量。the capacitor shall be stored at a temperature of 60±2℃ and relative huidity
		of 90 to 95% for 240±8hours。And then the capacitor shall be subjected to standard atmospheric
		conditions for 1 to 2hours, after which measurements shall be made.
		SPEC: 1)电容量变化Change in capacitance: ±20%初时值以内Within±20%of the initial value
		2)损耗正切角tangent of the loss angle:150%初始值规定以内within ± 150%of the
		initial value
		3)ESR (equivalent series resistance) : 150%初始值规定以内within ± 150%of the
7	高温储存	initial value
		4)漏电流leakage current: 小于等于初时值The initial specified value or less
		在+105温度下不外加电压储存, 电容器存放1000小时。然后在标准条件下放1到2小时进行测量, 并且
		在测漏电流前, 必须满足以上条件。The capacitor shall be stored at +105℃ temperature
		specified below for 1000 hours. During which time no voltage shall be applied. And then the
		capacitor shall be subject to standard atmospheic conditions for 1 to2hours, after which
		measurements shall be made, Prior to the measurement of leakage current, following conditioning
		may be made.
		SPEC: 1):电容量变化Change in capacitance: ±20%初时值以内Within±20%of the initial value
		2)损耗正切角tangent of the loss angle:150%初始值规定以内within ± 150%of the
		initial value
		3)ESR (equivalent series resistance) : 150%初始值规定以内within ± 150%of the
		initial value
		4)漏电流leakage current: 小于等于初时值≤The initial specified value or less

8	耐久性 load life	在+105℃下，电容器施加带纹波电流的额定电压3000小时。在标准条件下放1到2小时后进行测量。 The rated voltage with specified ripple current shall be applied continuously to the capacitor at maximum operating temperature +105℃ for 3000 hours. And then the capacitor shall be subjected to standard atmospheric conditions for 1to 2hours, after which measurement shall be made.
		SPEC: 1)电容量变化Change in capacitance: ±20%初时值以内Within±20%of the initial value
		2)损耗正切角tangent of the loss angle:150%初始值规定以内within ± 150%of the initial value
		3)ESR（equivalent series resistance）：150%初始值规定以内within ± 150%of the initial value
		4)漏电流leakage current: 小于等于初时值≤The initial specified value .
9	温度循环测试 Rapid temperature change	电容器要在图1的温度循环要求下保持5个循环，然后在标准条件下放1-2个小时后进行测量。 The characteristics of a capacitor kept under the temperature cycle indicated in Figure1 for 5 cycles . And then the capacitor shall be subjected to standard atmospheric conditions for 1to 2hours, after which measurement shall be made
		 Figure.1
		SPEC: 1)电容量变化Change in capacitance: ±10%初时值以内Within±10%of the initial value
		2)损耗正切角tangent of the loss angle:小于等于初时值≤The initial specified value
		3)ESR（equivalent series resistance）:小于等于初时值≤The initial specified value
		4)漏电流leakage current: 小于等于初时值≤The initial specified value .
10	低温测试 Low temperature test	电容器要在温度-55℃条件下存放72±2个小时。然后在标准条件下放1到2个小时进行测试。 the shall be stored at a temperature of -55℃ for 72±2hours. And then the capacitor shall be subjected to standard atmospheric conditions for 1 to 2hours, after which measurements shall be made
		SPEC: 1)电容量变化Change in capacitance: ±10%初时值以内Within±10%of the initial value
		2)损耗正切角tangent of the loss angle:小于等于初时值≤The initial specified value
		3)ESR（equivalent series resistance）:小于等于初时值≤The initial specified value
		4)漏电流leakage current: 小于等于初时值≤The initial specified value .
11	ON-OFF实验	在40±2℃的环境下，电压5V叠加纹波电流3A，通电10S，停1S，开关机，循环1000次。 Ther capacitor shall be subjected to 10000 cycles with voltage 5V & ripple 3A current at maximum operating temperature +40±2℃. each consisting of a charge period of 10sec, followed by a discharge period of approx.1sec
		SPEC: 1)电容量变化Change in capacitance: ±10%初时值以内Within±10%of the initial value
		2)损耗正切角tangent of the loss angle:小于等于初时值≤The initial specified value
		3)ESR（equivalent series resistance）:小于等于初时值≤The initial specified value
		4)漏电流leakage current: 小于等于初时值≤The initial specified value .

五:标志 Marking

⊖

⊕

① : Capacitance

② : Voltage

③ : Series

1,	代表容量 Rate Capacitance
2,	代表电压 Rate Voltage
3,	代表系列号Series

六: 包装 Packing

包装标签标示 Packing Label Marked

(下面项目应该体现在标签上 The following items shall be marked on the label)

(盘/内盒/外箱 Reel/inside box/outer carton)

系列	Series
物料编码	P/N
额定容值	Rate Capacitance
额定电压	Rate Voltage
数量	Quantity
尺寸	Size
批号	LOT Number

LOT Number:


第一码: Table 1

Code	A	B	C	D
Year	2016	2017	2018	2019

第二码：Table 2

Code								
Week								
Code								
Week								
Code								
Week								
Code								
Week								
Code								
Week								
Code								
Week								
Code								
Week								
Code								
Week								

■In-box&outer carton 内盒和外箱



◆Please order by minimum package quantity.

◆请以最小包装数量订购。

KNSCHA	Bag (pcs)	In-box (pcs)	Carton (pcs)
118EC485	500	4000	16000

七、	铝电解电容使用注意事项。Guidelines For Using Aluminum Electrolytic Capacitor. 为了使您获得电解电容的最佳性能和延长电解电容的使用寿命，在使用电解电容前，请务必阅读本注意事项。 Upon using Aluminum Electrolytic Capacitors, please proper handing and observing to following important points will insure optimum capacitor performance and long life.
1	直流电解电容是有极性的。DC electrolytic capacitors are polarized. 确定极性，极性标志在电容器的基体上。以免因极性反可能引起电路短路或电容器损坏，当极性不固定或不确定的，使用无极性电容器。注意直流电容器不能使用于交流。Make sure of the polarity. The polarity is marked to on the body of the capacitor .Application of the reversed voltage cause a short circuit or damage the capacitor. Use bipolar capacitors when the polarity is not determined or unknown. Note that DC electrolytic capacitors can not be used for AC application.
2	使用电压不要大于额定电压。Do not apply voltage Higher than rated voltage. 使用电压大于额定电压，漏电流会增大，可能损坏电容器。建议工作电压为额定电压的70%-80%，电容器在建议工作电压下使用可以延长电容器的寿命。If a voltage exceeding the rated voltage is applied, the leakage current will increase, which damage the capacitor. Recommended working voltage is 70 to 80 percent of rated voltage. Using capacitors at recommended working voltage prolongs capacitor life.
3	不要使用过量纹波电流通过电容器。Do not allow excessive ripple current through the capacitor. 流过电容器的纹波电流超过许可值，将会引起电容器发热，电容量减少，损耗电容器。通过电容器的纹波电流不要大于允许值。The flow of ripple current over permissible ripple current will cause heat of the capacitor, which may decrease the capacitance and damage the capacitor. Ripple current on the capacitor must be at or below allowable level.
4	快速充放电电路中，使用专门设计的电容器。Use specially designed capacitors for the circuits where charge and discharge are frequency repeated. 在经受快速的周期性充放电电路中，电容器可能收到损害，它的寿命因容量下降、温升等原因而缩短，在这种电路中，一定要使用专门设计的电容器。In the circuit subjected to rapid charge cycles, capacitors may be damaged, its life may be shortened by capacitance decrease, heat rise, ect. Be sure and use special capacitors in these applications.
5	工作温度范围。Operating temperature range. 电容器的特性随工作温度变化而变化，在温度较高的情况下，容量，漏电流增大，损耗减少；在低温情况下，容量和漏电流下降，损耗增大。电容器在较低温度下使用会确保延长寿命。The characteristics of capacitors change with the operating temperature. The capacitance and leakage current increase and $\tan\delta$ decrease at higher temperatures. The capacitance and leakage current decrease and $\tan\delta$ at increase lower temperature. Usage at lower temperature will ensure longer life.
6	核对工作频率。Check operating frequency. 电解电容器的容量通常是在100HZ或者120HZ下测得的。然而要记住容量随频率的升高而下降，$\tan\delta$ 随频率的升高而增大，并使周围温度升高。The capacitance of electrolytic capacitors is usually measured at 100Hz or 120Hz. However, remember that capacitance decrease and $\tan\delta$ increase as the applied frequency becomes higher whereas the ambient temperature becomes higher.
7	长时间存放的电容器，在使用前加额定直流电压处理。 Apply rated DC voltage treatment to the capacitors which have been stored for a long time. 长时间的存放，实际对电容器的容量和$\tan\delta$没有多大的影响，然而往往会使漏电流增大，耐压降低。长时间存放后的电容器处理，首先逐渐施加直流电压至额定电压，然后再使用。Long periods of storage have virtually no effect on a capacitor's capacitance and $\tan\delta$. Such periods tend however, to increase leakage current and decrease withstand voltage. After removing capacitors from long-duration storage, first apply a gradually increasing DC voltage to rated voltage and then use them.
8	电容器外壳与极性不是绝缘的。The capacitor case is not insulated from the cathode terminal. 电容器的外壳与极性是通过电解液连接的，则电容器的外壳必须与线路绝缘，电容器的安装位置处一定要采取绝缘措施。

8,	The capacitor's case and cathode terminal connect through the electrolyte. If the case is to be completely insulated, that insulation must be at the capacitor's mounting point.
9,	电容器的端子或者引线上不要施加过大的力。
	Do not apply excessive force to the terminals and leads.
	过大的力施加到端子和引线上，可能引起引线的断裂或端子分裂，转而会引起内部链接的破坏
	The excessive strong force applied to the terminals and lead wires may cause leads to break or
	terminals to separate and, in turn, cause the internal contact to fail.

有害物质目录表

Hazardous substances management table of contents

区分 Type	物质名称（中文名） Name(chinese)	物质名称(英文名) Name(English)	有害物质包含与否 (Test result)	
			有 Yes	无 No
Level A- I	铅以及它的化合物	Lead and its compounds		NO
	镉以及它的化合物	Cadmium and its compounds		NO
	水银以及它的化合物	Mercury and its compounds		NO
	六价铬以及它的化合物	Hexavalent chromium ang its compounds		NO
	多溴化的联苯	Polybrominated biphenyls		NO
	聚溴二苯醚	Polybrominated diphenylethers		NO
Level A- II	多氯化联苯（PCB）	Polybrominated biphenyls（PCB）		NO
	多氯化萘（PCN）	Polybrominated naphthalenes(PCN)		NO
	三磷酸盐	Polybrominated terphenyls(PCT)		NO
	氯化涂石蜡（SCCP）	Short-chain chlorinated paraffins(SCCP)		NO
	石棉以及它的化合物	Asbestos ang its compounds		NO
	臭氧层破坏物质	Ozone Depleting Substances		NO
	偶氮化合物	Azo compounds		NO
	镍以及它的化合物	Specific organic tin compounds		NO
	有机锡类化合物	Nickel and its compounds		NO
	砷以及它的化合物	Specific organic tin compounds		NO
	甲醛	Formaldehydes		NO
Level B	氯化乙烯树脂	Polyvinyl chloride,(PET)		NO
	磷苯二甲酸盐	Phthalates		NO
	铍以及他的化合物	Berylium and its compounds		NO
	锑及其它的化合物	Antimony and its compounds		NO
	硒及其它的化合物	Selenium and its compounds		NO
	钯及其它的化合物	Palladium and its compounds		NO
	铋及其化合物	Bismuth and its compounds		NO
	其他氯类难燃试剂	Other chlorinated flame retardants		NO
	其他溴类难燃试剂	Other brominnated flame retardants		NO
Note:				
	1，原则上按照公司的管理规定，但由管理总部提出根据Buyer等交易商的要求制定的另行有害物 质管理目录来执行的要求时，应优先按照管理总部的管理目录来记载。			
	2，确认合作企业现在是否在使用这类物质，应记录使用与否。			